



## **High Clear PET Cold Laminating Film**

## PRODUCT: HPETC3625 Features& Applications:

- High clear & glossy PET film with PET release liner, 100% PVC free
- Solvent polyacrylate adhesive, permanent& transparent
- Premium quality and excellent dimensional stability

## **MATERIAL DETAILS**

WATERIAL DETAILS			
PROPERTIES	TEST METHOD	RESULTS	
Film thickness	ISO 4591:1992	36micron high clear PET film	
Thickness with adhesive	ISO 4591:1992	56micron	
Adhesive type		Solvent polyacrylate, permanent, transparent	
Release paper		25micron PET film	
Dimensional stability	FINAT TM14	Adhered to glass, no shrinkage in cross direction & in length	
Temperature resistance		Adhered to aluminum20 $^{\circ}{\mathbb C}$ to +65 $^{\circ}{\mathbb C}$ , no variation	
Seawater resistance	DIN 50021	Adhered to aluminum, after 48h/23℃, no variation	
Adhesive power	FINAT TM1, after 24h,stainless steel	After 24h,stainless steel 8-12N/25mm	
Tensile strength along acorss	ASTM D882-02;200MM/MIN	min.18MPa min.18MPa	
Elongation at break along across	ASTM D882-02;200MM/MIN	min 120% min 140%	
Shelf life		1 year	
Application temperature		Min.+10℃	
Service life by specialist application Under vertical outdoor exposure (normal climate of China)		1 year	
Available Width		1.27/1.37/1.52m	
Regular Length		50m	

## **INK PRINTABILITY**

Solvent	Eco Solvent	UV	Latex
Screen Printing	Dye-sub Transfer	Dye-sub Direct	Water based

NOTE: All above information shall only used as a guide; buyers shall independently test and determine the products suitability. The mentioned data are average of test result and should not be used for the purpose of lawsuit or warranty

(Soyang Headquarter)	Soyang Technical Textile (Zhejiang) Co., Ltd	Soyang Europe Ltd
West 19th FL, Yongtong Information plaza, No. 141 Huancheng Bei Road, Hangzhou City, Zhejiang PR., China.	No.36 Jinniu Road, Jianshan District, Haining City, Zhejiang PR, China.	Calder House Metcalf DriveAltham Industrial estateAltham Lancashire BB5 5TU UK
www.soyang.net	Hangzhou Soyang Flexible Material Co., Ltd	www.soyang.co.uk
P. 0086-571-28918690		P. 0044 (0) 161 765 3400
F. 0086-571-28918695	No.1199 Gongyuan Xi Rd. Fuyang, Hangzhou City, Zheijang, PR. China	F. 0044 (0) 1282 772982