



TECHNICAL DATA SHEET



Glossy Cold Lamination Film

PRODUCT: EC6001G

Features:

- 70±5micron monomeric PVC Film, Glossy
- Solvent polyacrylate, transparent& permanent adhesive
- 100±5gsm single side PE-coated silicon paper

MATERIAL DETAILS

PROPERTIES	TEST METHOD	RESULTS
Film Material	ISO 4591:1992	70±5um monomeric PVC Film, Glossy
Adhesive type		Solvent polyacrylate, transparent& permanent adhesive
Release Liner		100±5gsm single side PE-coated silicon paper
Dimensional stability	FINAT TM14	Adhered to steel, 0.20mm max in cross direction, in length 1.0mm max.
Temperature resistance		Adhered to aluminum, -20℃ to +65℃, no variation
Seawater resistance	DIN 50021	Adhered to aluminum, after 48h/23℃ no variation
Adhesive power	FINAT TM1	10-14 N/25mm
Tensile strength along across	ASTM D882-02;200MM/MIN	min.18MPa min.18MPa
Elongation at break along across	ASTM D882-02;200MM/MIN	Min120% Min140%
Storage Condition		out of direct sunlight at 23℃ and 50% humidity
Application temperature		Min.+10℃
Shelf Life		1 year
Available Width		0.914/1.07/1.27/1.37/1.52m
Regular Length		50m

INK PRINTABILITY

Solvent	Eco Solvent	UV	Latex
Screen Printing	Dye-sub Transfer	Dye-sub Direct	Water based

NOTE: All above information shall only used as a guide; buyers shall independently test and determine the products suitability. The mentioned data are average of test result and should not be used for the purpose of lawsuit or warranty

**Soyang Technologies Co., Ltd
(Soyang Headquarter)**

West 19th FL, Yingtong Information plaza, No. 141 Huancheng Bei Road, Hangzhou City, Zhejiang PR., China.

www.soyang.net

P. 0086-571-28918690

F. 0086-571-28918695

Soyang Technical Textile (Zhejiang) Co., Ltd

No.36 Jinniu Road,Jianshan District,Haining City, Zhejiang PR,China.

Hangzhou Soyang Flexible Material Co., Ltd

No,1199 Gongyuan Xi Rd, Fuyang, Hangzhou City, Zhejiang, PR, China

Soyang Europe Ltd

Calder House Metcalf DriveAltham Industrial estateAltham Lancashire BB5 5TU UK

www.soyang.co.uk

P. 0044 (0) 161 765 3400

F. 0044 (0) 1282 772982