

# Dura Tent



Soyang's comprehensive range: PVC-Free. Supported by full industry chain. Compatible with various printing methods.

## ST-315T/ST-315D

### BRIEF DESCRIPTION

- 100% polyester woven fabric, 600Dx600D base with tight structure & very good strength
- Widely used as parasol, beach chair, banner, curtain, roll-up, table cloth, pillow, bed cover & upholstery

### FEATURES



PVC-FREE



PHTHALATE FREE



TIGHT STRUCTURE

### INK PRINTABILITY



### MATERIAL DETAILS

| PROPERTIES                     | TEST METHOD                     | METRIC          | IMPERIAL         |
|--------------------------------|---------------------------------|-----------------|------------------|
| Total Weight                   | DIN EN ISO 2286-2, ASTM D751    | 220 g/sq.m      | 6.5 oz/sq.yd     |
| Base Fabric                    | DIN 60001, ASTM D7641           | 100%polyester   | 100%polyester    |
| Yarn Dtex                      | DIN EN ISO 2060, ASTM D1907     | 660x660 dtex    | 600x600denier    |
| Weave Method                   | N/A                             | Woven           |                  |
| Shrinkage                      | ISO 9866-2-1991                 | ≤2%             |                  |
| Shielding Rate                 | ANSI PH2.19, ISO 5/2            | 56%             |                  |
| Tensile Strength               | DIN EN ISO 1421                 | 2100x1610 N/5cm | 240x184 lbs/inch |
| Tear Strength                  | DIN53363                        | 264x189 N       | 59x43 lbs        |
| Recommend Fixation Temperature | N/A                             | 190°C, 30s      |                  |
| Width Available                | DIN EN ISO 3759, ASTM D751-2006 | Max 320cm       | 126"             |
| Standard Length                | DIN EN ISO 3759, ASTM D751-2006 | 50m             | 55yds            |

NOTE: It is normal that the weight of most products will have an average fluctuation of 5%. All above information shall only used as a guide; buyers shall independently test and determine the products suitability. The mentioned data are average of test result and should not be used for the purpose of lawsuit or warranty.

