

Memphis Pro Backdrops

Soyang's comprehensive range: PVC-Free. Supported by full industry chain. Compatible with various printing methods.

ST-2102T/ST-2102D

BRIEF DESCRIPTION

- 100% warp-knitted polyester fabric with white surface and grey back
- Perfect opacity keeps it ideal as backdrops
- Light stretch & truly crease free, easy for transportation and installation
- Highly recommended to be used as frame, stretch display, light curl geometric, grandformat, etc

FEATURES



PVC-FREE



PHTHALATE FREE



WRINKLE-RESISTANT



GOOD OPACITY



SLIGHT STRETCH

INK PRINTABILITY



MATERIAL DETAILS

| PROPERTIES | TEST METHOD | METRIC | IMPERIAL |
|--------------------------------|--|-----------------------------------|-------------|
| Total Weight | DIN EN ISO 2286-2, ASTM D751 | 340 g/sq.m | 10 oz/sq.yd |
| Base Fabric | DIN 60001, ASTM D7641 | 100%Polyester | |
| Weave Method | N/A | Warp-knitted | |
| Shrinkage | ISO 9866-2-1991 | ≤2% | |
| Shielding Rate | ANSI PH2.19, ISO 5/2 | 99% | |
| Elasticity | Length*Width=200*50mm, Speed=100mm/min, Tension=20N | Warp: 9% Weft: 7% | |
| Flame Resistance | EN13501-1, DIN 4102-1-B1, NFPA 701 | EN13501-1,DIN 4102-1-B1, NFPA 701 | |
| Recommend Fixation Temperature | N/A | 190°C, 30s | |
| Width Available | DIN EN ISO 3759, ASTM D751-2006 | Max 320cm | 126" |
| Standard Length | DIN EN ISO 3759, ASTM D751-2006 | 50m | 55yds |

NOTE: It is normal that the weight of most products will have an average fluctuation of 5%. All above information shall only used as a guide; buyers shall independently test and determine the products suitability. The mentioned data are average of test result and should not be used for the purpose of lawsuit or warranty.