

Stretch Revolution



ST-145T/ST-145D

Soyang's comprehensive range: PVC-Free. Supported by full industry chain. Compatible with various printing methods.

BRIEF DESCRIPTION

- 100% warp-knitted polyester fabric
- Lighter weight, but still keeps the good opacity
- Even stretch, widely be used as stretch display, tradeshow, etc

FEATURES



INK PRINTABILITY



MATERIAL DETAILS

PROPERTIES	TEST METHOD	METRIC	IMPERIAL
Total Weight	DIN EN ISO 2286-2, ASTM D751	230 g/sq.m	6.8 oz/sq.yd
Base Fabric	DIN 60001, ASTM D7641	Polyester	Polyester
Weave Method	N/A	Warp-knitted 2 bar	
Shrinkage	ISO 9866-2-1991	≤2%	
Shielding Rate	ANSI PH2.19, ISO 5/2	63%	
Elasticity	Length*Width=200*50mm, Speed=100mm/min, Tension=20N	Warp:10%	Weft:10%
Flame Resistance	DIN 4102-1-B1, NFPA 701 Test1	DIN 4102-1-B1, NFPA 701 Test1	
Recommend Fixation Temperature	N/A	190°C, 30s	
Width Available	DIN EN ISO 3759, ASTM D751-2006	Max 320cm	126"
Standard Length	DIN EN ISO 3759, ASTM D751-2006	50m	55yds

NOTE: It is normal that the weight of most products will have an average fluctuation of 5%. All above information shall only used as a guide; buyers shall independently test and determine the products suitability. The mentioned data are average of test result and should not be used for the purpose of lawsuit or warranty.

