

Best-value Laminated Tent Fabric 15oz/510gsm

TFL5599

Soyang's industrial technical textiles series offers tailored solutions with the broadest range and top-tier quality.

BRIEF DESCRIPTION

- Good tensile and tear strength
- Good stretch ability and softness
- Ideal for general mobile constructions aiming for medium-term applications

FEATURES



MATERIAL DETAILS

| SPECIFICATIONS | TEST METHOD | RESULTS |
|-------------------------------------|--------------------|-------------------------------|
| SILCINCATIONS | | NESOEIS |
| Composition | DIN 53830 DIN60001 | 550 x 550 Dtex 3.5 x 3.5/cm |
| | ASTM D 751 | 500D x 500D 9 x 9/inch |
| Weight | DIN53352 | 510gsm ± 20gsm |
| | ASTM D 751 | 15.8oz |
| Lacquering | | 1/1 Acrylic (Upon request) |
| Surface Finish | | Glossy |
| Color | | White |
| Breaking Strength (Warp x Weft) | DIN 53354 | 872 x 662 N/5cm |
| | FS 5100 | 198 x 150 lbs/2" |
| Tearing Strength (Warp x Weft) | DIN 53363 | 163 x 149 N |
| | FS 5100 | 37 x 33 lbs |
| Width | | 1000 - 3200mm |
| | | 36" - 126" |
| Fire Resistance | | B1, B2, NFPA 701 |
| Temperature Resistance | DIN 53372 | - 30 ℃ - 70 ℃ |
| | FS 5874 | -20° F - 158° F |

NOTE: All characteristics could be customized upon request, such as fire retardant, higher color fastness etc. All above information shall only be used as a guide; buyers shall independently test and determine the products' suitability. The mentioned data are the average of the test results and should not be used for the purpose of a lawsuit or warranty.