

# **Nightstar Phoenix Blackback**

ST-2166T/ST-2166D

Soyang's comprehensive range: PVC-Free. Supported by full industry chain. Compatible with various printing methods.

## **BRIEF DESCRIPTION**

- 100% polyester warp-knitted fabric, ultra-white & smooth surface with a luxurious texture
- High-performing anti-scratch black coated back offers 100% opacity
- Very soft hand feel and truly crease free, super easy installation with ideal stretch
- Width up to 5meters, highly recommended to be used as backdrop, Pop-up, frame, exhibition&event, display system, etc

## **FEATURES**













### **INK PRINTABILITY**





### **MATERIAL DETAILS**

| PROPERTIES                     | TEST METHOD   | METRIC                                      | IMPERIAL      |
|--------------------------------|---|---|---------------|
| Total Weight                   | DIN EN ISO 2286-2, ASTM D751                        | 240g/sq.m                                   | 7.1 oz/sq.yd  |
| Base Fabric                    | DIN 60001, ASTM D7641                               | 100%polyester                               |               |
| Weave Method                   | N/A   | Warp-knitted                                |               |
| Shrinkage                      | ISO 9866-2-1991                                     | Warp: 3.5%-4%                               | Weft: ≤2%     |
| Shielding Rate                 | ANSI PH2.19, ISO 5/2                                | 100%  |               |
| Elasticity                     | Length*Width=200*50mm, Speed=100mm/min, Tension=20N | Warp: (6±2)% \                              | Weft: (10±2)% |
| Flame Resistance               | EN13501-1, DIN 4102-1-B1,<br>NFPA 701 Test1         | EN13501-1, DIN 4102-1-B1,<br>NFPA 701 Test1 |               |
| Recommend Fixation Temperature | N/A   | 190°C-200°C, 30s-50s                        |               |
| Width Available                | DIN EN ISO 3759, ASTM D751-2006                     | Up to 500cm                                 | Up to 197"    |
| Standard Length                | DIN EN ISO 3759, ASTM D751-2006                     | 50m   | 55yds         |

NOTE: It is normal that the weight of most products will have an average fluctuation of 5%. All above information shall only be used as a guide; buyers shall independently test and determine the products suitability. The mentioned data are average of test result and should not be used for the purpose of lawsuit or warranty.







